

SPECIFICATIONS ISOVISTA® LONGFORMAT PANELS FROM 100 / 120 / 140 / 160 mm

| SPECIFICATIONS ACCORDING | TECHNICAL VALUE | UNIT |
|--------------------------|-----------------|------|
|--------------------------|-----------------|------|

GENERAL CHARACTERISTICS

| | | |
|--|-----------------|--------------------|
| Lenght | 131,5 | mm |
| Width | 54,5 | mm |
| Thickness | 100/120/140/160 | mm |
| N. surface developed by 1 panel | 0,51 | m ² |
| N. surface developed by 1 corner panel | 0,38 | m ² |
| N. surface developed by 1 linear meter of corner panels | 0,76 | m ² |
| Orthogonality | ± 2/1000 | mm/mm |
| Flatness | ± 5 | mm |
| Dimensional stability under normal laboratory conditions | ± 0,2 | % |
| Declared thermal conductivity al 10 °C of the component | 0,034 | W/mK |
| Thermal resistance of the panel (slip + EPS insulation) | | |
| 100 mm | 2,557 | m ² K/W |
| 120 mm | 3,145 | m ² K/W |
| 140 mm | 3,733 | m ² K/W |
| 160 mm | 4,308 | m ² K/W |
| Thermal transmittance (slip + EPS insulation) | | |
| 100 mm | 0,39 | W/m ² K |
| 120 mm | 0,32 | W/m ² K |
| 140 mm | 0,27 | W/m ² K |
| 160 mm | 0,23 | W/m ² K |
| Resistance to bending | ≥ 170 | kPa |
| Reaction to fire | B-S1-D0 | Class |

SPECIFIC CHARACTERISTICS

| | | |
|---|---------------|-------------------|
| Compressive stress at 10 % strain | ≥ 120 | kPa |
| Factor of resistance to water vapor diffusion | 30-70 | μ |
| Water absorption for a long period of immersion | ≤ 2 | % |
| Water absorption by partial immersion | ≤ 0,5 | Kg/m ² |
| Water vapor permeability | 0,010 - 0,024 | mg/(Pa·h·m) |
| Specific heat capacity | 1260 | J/(Kg·K) |
| Apparent density with grouting | 22,00 | Kg/panel |
| Limit temperature of use | 75 | °C |

SPECIAL EXPERIMENTS CARRIED OUT

| | | |
|---|-----|----------|
| Shear bond slip/panel | 526 | Kg/panel |
| Tensile strenght to fixing panel/standard wall | 524 | Kg/panel |
| Cycles of thermal stress (8h at -20°C - 8h at 30°C / 50% moisture - 8h at 80°C / 90% moisture) | | |
| Weight changes | 4 | ‰ |
| Variations in shape | 1 | ‰ |